

EVA Foam Rolls (81kg/m³)



Colour		Grey, Black
Compression Set (Room Temp 22hr)	ASTM D1056	70%
Tensile Strength	JIS K6767	6.0-9.0 kg/cm ²
Elongation	JIS K6767	80-120%
Hardness		12 ShoreA (+/-2)
Surface		Plain both sides
Density	JIS K6767	0.10 + 0.02 g/cm ³
Tear Strength	JIS K6767	2.0-4.0 kg/cm ²

Chemical Composition:

- Ethylene Vinyl Acetate (EVA) Resin
- Polyethylene Resin
- Calcium Carbonate
- Zinc Oxide
- Azodicarbonamide
- Dicumyl Peroxide
- Steric Acid
- Pigment (colours)