

EVA Foam Sheet (81kg/m³)



| | | |
|---|-------------|-------------------------------|
| Colours | | Grey, Blue, Black |
| Compression Set (Room temp 22hr) | ASTM D1056 | 70% |
| Temperature Range | | -10°C - +70°C (approx.) |
| Tensile Strength | JIS K6767 | 6.0-9.0 kg/cm ² |
| Elongation | JIS K6767 | 80-120% |
| Hardness | | 12 ShoreA (+/-2) |
| Surface | | Plain both sides |
| Density | JIS K6767 | 0.10 + 0.02 g/cm ³ |
| Tear Strength | JIS K6767 | 2.0-4.0 kg/cm ² |
| Structure | Closed Cell | |

Chemical Composition:

- Ethylene Vinyl Acetate (EVA) Resin
- Polyethylene Resin
- Calcium Carbonate
- Zinc Oxide
- Azodicarbonamide

- Dicumyl Peroxide
- Steric Acid